

S1 1 PN='JP 06192579'
? t1/7/1

1/7/1
DIALOG(R)File 350:Derwent WPIX
(c) 2003 Thomson Derwent. All rts. reserv.

009993013 **Image available**
WPI Acc No: 1994-260724/199432
Asphalt paving compsn. - contains maleic anhydride-modified polyethylene
or polypropylene
Patent Assignee: SHOWA SHELL SEKIYU KK (SHEL)
Number of Countries: 001 Number of Patents: 001
Patent Family:
Patent No Kind Date Applicat No Kind Date Week
JP 6192579 A 19940712 JP 92358162 A 19921225 199432 B

Priority Applications (No Type Date): JP 92358162 A 19921225

Patent Details:

Patent No	Kind	Lan	Pg	Main IPC	Filing Notes
JP 6192579	A		5	C08L-095/00	

Abstract (Basic): JP 6192579 A

Compsn. contains 0.1-5.0 wt.% maleic anhydride modified
polyethylene or polypropylene in asphalt. The maleic anhydride modified
polyethylene or polypropylene has a mol. wt. of 1000-20000 and an acid
value of 3-70, pref. 20-60mg KOH/g. The modified polyethylene or
polypropylene is obtd. by reacting 0.5-15 wt.% of maleic anhydride with
polyethylene or polypropylene.

The asphalt for the compsn. is at least one of straight asphalt,
blown asphalt, propane-deasphalted asphalt, polymer-modified asphalt
and synthetic asphalt pref. having a needle penetration of 20-100.

ADVANTAGE - Sepn. of aggregate and asphalt does not occur.

Dwg.0/0

Derwent Class: A93; H08; L02

International Patent Class (Main): C08L-095/00

International Patent Class (Additional): C08L-023-02; C08L-095/00

?